

Öko Skin Characteristics



Technical Specifications*

	Öko Skin	Standard
Size	1800/147 mm	
Dimensional variation length	± 2,0 mm	EN 12467
Dimensional variation width	± 1,0 mm	EN 12467
Thickness	13 mm	
Thickness tolerance	-1,0 mm /+2,0 mm	
Thickness tolerance within an shipment	± 1,3 mm	EN 12467
Edge straightness (Level 1)	± 0,05 %	EN 12467
Perpendicularity (Level 1)	± 2 mm/m	EN 12467
Physical characteristics		
Swelling	0,384 mm/m	
Shrinkage	0,737 mm/m	
Bulk density	2,0 - 2,42 kg/dm ³	
Bending tensile strength	> 18,5 N/mm ² (MOR)	EN 12467, Category 4
Elastic modulus	approx. 10.000 N/mm ²	
Dead load / Mass per unit area (13 mm)	26 - 31,5 kg/m ²	
Thermal expansion coefficient	10*10 ⁻⁶ 1/°k	DIN 51045
Building material class	A1 - incombustible	DIN 4102 EN 13501
Temperature stability	according to humidity up to 350°	
Specific heat capacity	approx. 1.000 Joule / (kg * K)	
Conductivity	lambda: ca. 2,0 W / (m * K)	
Weather-resistance		
Water impermeability	given	EN 12467
Heat-rain-alternate test	given	EN 12467
Frost resistance	given	EN 12467
Frost-defrost-alternate test	given	EN 12467
UV-light resistance	light-, UV-colour pigments	DIN 12878
Hot water resistance	given	EN 12467
Wet storage resistance	given	EN 12467
Fastening visible	rivets, screws	
Fastening not visible	adhesive	
Substructure	aluminium, steel, wood	
Joint width	min. 8 mm	

Reinforcement

Edge formation

With alkali-resistant glassfibres in the matrix (Cem-FIL, Approval Z-3.72-1731)

Cut edges are unfinished and sharp-edged with a coarseness of about 1 mm on the visible face. Glassfibres may emerge at the edges

** MOR: Modus of Rupture; Design values deviate from MOR in accordance with national rules and regulations. National approvals, rules and regulations apply to the calculation of the rated resistance.

Colours

Surfaces

Bianco
Ivory
Silvergrey
Anthracite
Liquide Black

Sandstone
Terra
Mocca Brown
Terracotta
Green

SA sandsblasted, vivid surface

Colour, Design & Surface

Because concrete is a natural product, each glassfibre reinforced concrete panel is regarded as a single piece. Differences in colour, structure and texture are characteristic and intended.

Efflorescences or small, visible pores are not defects. The light resistance varies depending on the colour. Differences in the surface appearance, which do not affect the fitness for purpose of the panels, are permitted. EN 12467 / Data sheet Exposed concrete 02/2004 [Publisher.:BDZ/DBV]

* Subject to the particular quotation documentation.

The information contained in this document and the technical description of product characteristics and the technical instructions for their use should not be interpreted as a contractual commitment on the part of the manufacturers. Despite careful inspection, no liability can be accepted for the correctness, completeness and topicality of the document. This is particularly true for typographical errors or subsequent changes to technical specifications.

Colours & Surfaces

Many design options

Öko Skin offers a wide range of design options for facades and decorative applications. The selection of ten different colours offers a wide range of designs to meet individual expectations. Glassfibre concrete is a natural material. The raw materials used for its production create a unique surface finish that is characteristic of concrete. This play of colours within a certain colour shade is intentional and enhances the vivid character of concrete as natural building material.

Natural colours

Öko Skin has a distinct advantage over other colour-treated materials - namely the consistent colouring of the whole panel. The mixture of the desired colour is created before the actual production process. The colour becomes part of the product by being added in the blending of the raw materials. Other products are in some cases only superficially treated and coloured, resulting in significant quality differences.

Öko Skin is coloured by ferric oxide colours and natural additions and subsequently sandblasted. The natural, authentic colours of Öko Skin fit well in landscapes and blend with nature and the environment.

Colour fastness and UV stability

Liquid colours for colouring cement-bonded building materials comply with the DIN EN 12878. The pigments used in the liquid colours are light-, UV- and weather-resistant and not soluble in water, alkalis or diluted acids. Factors such as natural fluctuations in raw materials used, panel and air moisture, dirt and light sources must be taken into consideration. The appearance of the panels may even become brighter due to dehydration. Changes caused by age, weather or environment specific influences are natural processes that cannot be influenced from a production point of view and are therefore not considered material defects. The technical characteristics of the panel are not affected by these.

Colour differences in production batches

Glassfibre reinforced concrete is a natural material. The characteristics of the raw materials such as the colour of cement lead to variations in colour within a panel, between individual panels or between different production batches.

Due to technical reasons printed colours may differ from the original shade.

Colours


01 | Bianco




02 | Ivory




03 | Silvergrey



04 | Anthracite




05 | Liquide Black




06 | Sandstone



07 | Terra




08 | Mocca Brown



09 | Green




10 | Terracotta



Surface

SA | Sandblasted



The surface of Öko Skin is sandblasted and creates a vivid surface.

Characteristics of Öko Skin

Vivid signs of a natural building material

Concrete is a natural product and Rieder sees it as such, with all its vital signs and characteristics. Living surfaces with the interplay of colour shades and light cloud effects, rather than dead and clinical surfaces are characteristic of Öko Skin. Even in the colouring of the concrete matrix, the focus is placed on meeting the ecological requirements of modern design. This is why the production involves natural raw materials to ensure the authenticity of all products. The demand for low porosity, homogeneous colour and strictly uniform smooth surfaces is not part of our sustainable philosophy. We consciously avoid chemical treatment and artificial materials to preserve the authenticity of the „green“ product Öko Skin. Colour and texture variations are a feature of our natural product.

Concrete lives

As the panels are not chemically treated or painted, small defects, dents, tension lines, efflorescences or flaws and textures may be visible (Data sheet exposed concrete 02/2004 [Publ.:BDZ/DBV]).

When cement sets, it separates calcium hydroxide. This dissolves in water and can migrate to the concrete surface. When the water evaporates, the calcium hydroxide is returned to the surface and is converted to calcium carbonate (lime). If this natural process is intensified by unfavourable conditions, it leads to deposition of calcium carbonate, which is visible as a white efflorescence. Efflorescences are a natural feature of all cement-bonded composite materials.

Part of nature - resistant & stable

Glassfibre reinforced concrete is not an artificially created material that exists cut off from the natural cycle of the environment. As adaptable and extraordinary the concrete skin is, it is just as authentic. Öko Skin is part of a natural cycle. Influencing variables for possible colour changes are temperature variations and differences in air humidity.

Concrete is hygroscopic. It absorbs moisture and gives it off again irregularly.

A typical feature of highly-compressed, high-quality concrete surfaces is so-called blue- and green discoloration, which can occur in particular in bright colours or fresh panels. They can be attributed to a natural hardening and drying process of organic substances. Tests and experiences have shown that this blue colouring on the cladding may disappear under the influence of UV and light. This occurs based on the climatic and environmental influences. Heat, insolation and dryness can in particular accelerate the process.

Note:

The surface characteristics described apply to the visible side of the cladding panel. Öko Skin sample panels can never reflect all of the above characteristics. In large-scale cladding applications, optical phenomena occur that cannot be detected on small sample panels.

Visual changes like micro-cracks do not affect the technical characteristics of Öko Skin. The static functions, the long-term stability and fire resistance are not affected.

